



INDUSTRIAL



# INDUSTRIAL 1210 FOG OUT FLAT

Interior • Acrylic Water - Based Flat Finish

## Product Data Sheet

Edition January 8, 2015



CROWN  
PAINT

### Product Description

Industrial 1210 Fog Out a specialty water-based acrylic flat dry fall designed for commercial ceilings. Overspray dries to powder after falling approximately 12 feet. Fog Out properties will depend on an ambient temperature and humidity.

### Certification

SCAQMD - complies with Rule 1113, Architectural Coating  
LEED - complies with GS-11 / EQ 4.2.  
MPI - #118

### Recommended Uses

Industrial and commercial ceilings where good hide and adhesion are required.

### Bases

Special order, white and pastels only.

### Packaging

Five gallon containers

### Finish

Flat, sheen @ 85° = 2 %

### Surface Preparation

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority. To ensure proper adhesion, the surface to be painted must be free of dirt, dust, oil, grease, wax, rust, and any other surface contaminants. Clean surface using an appropriate cleaner. Rinse thoroughly and allow to dry. Sand or scrape surface to remove any loose paint and to smooth old surfaces. Dull glossy surfaces by using 150 grit sandpaper. Fill cracks and holes with spackling paste to smooth uneven areas. When dry, sand and remove sanding dust.

**Masonry, Concrete Block:** All new surfaces must be cured according to the supplier's recommendations—usually at least 30 days – and have a pH between 7 and 10. Remove all form release and curing agents, efflorescence, salts, laitance, and other foreign matter. Patch cracks and holes with an appropriate filler. Rough surfaces may be filled to provide a smooth surface.

**Wood, Pre-Primed Fiberboard, Hardboard, Plywood:** Sand any exposed wood to a fresh smooth surface. Patch all holes and imperfections with a wood filler or putty and sand smooth. Remove all sanding dust.

**Aluminum and Galvanized Metal:** Wash with appropriate cleaner to remove any oil, grease, or other surface contamination using a water-based cleaner-degreaser. Remove all corrosion with sandpaper, steel wool, or other abrading method.

### Primer

•Concrete : **1040 MASONRY PRE-COAT**  
•Wood • Ferrous Metal • Non-Ferrous Metal: **1420 ONE PRIME**

### Application

**Temperature** (air, surface, and material) 12.8°C (55°F) and relative humidity below 80%.

**Spray only.**

**Airless Spray:**

Pressure - 2000 psi, Tip - .015"-.021", Reduction - Not recommended.

### Drying Time

Touch: 15-20 minutes

### Coverage

300-350 square feet per gallon, depending on surface

### Mil Thickness

Wet - 4.4 • Dry - 1.5

### Thinning

**DO NOT THIN**

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.



# INDUSTRIAL 1210 FOG OUT FLAT

Interior • Acrylic Water - Based Flat Finish



## Product Data Sheet

Edition January 8, 2015



# INDUSTRIAL



### Flash Point

N/A

### Clean Up

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

### Cautions

- Protect from freezing
- Non-photochemically reactive

### Composition

Titanium Dioxide 13.1%, Extenders 27.9%  
**TOTAL PIGMENT 41%**  
 Acrylic Resin 10%, Additives / Solvents 6.5%, Water 42.5%  
**TOTAL VEHICLE 59%**

Weights & Measurements +/-3.0%,  
 Solids by Volume: 41.7%,  
 Solids by Weight: 61%  
 VOC: 18 g/l  
 Weight Per Gal: 11.6 lbs.  
 Viscosity: 90-94 KU

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance and offered in good faith. All technical information is subject to change without prior notice. This product is guaranteed to give satisfactory performance if applied and used in accordance with the label instructions. Any liability shall be limited to a refund of the purchase price, or replacement of this product. This warranty does not include labor or cost of labor for the application of any coating. All express and all implied warranties are hereby disclaimed and excluded including all implied warranties of fitness for a particular use and merchantability. Final determination of the suitability of product or intended use is the sole responsibility of the user. Additional information may be obtained from your local sales representative.